

CEPSASFALT 60/70

Asphalt bitumen that complies with the specifications in the standard ASTM D-946 for B 60/70 bitumen.

SPECIFICATIONS

Characteristics	Unit	Standard	MIN	MAX
Fresh binder				
Penetration (25°C)	0,1 mm	ASTM D5	60	70
Ductility	cm.	ASTM D113	100	--
Solubility	%	ASTM D2042	99,0	--
Flash point	°F	ASTM D92	450	--
Resistance to hardening at 163°C (ASTM D1754)				
Retained penetration	%	ASTM D5	47	--
Ductility	cm.	ASTM D113	75	--

RECOMMENDED WORKING TEMPERATURES

- > Mixing temperature (°C): 150 - 160.
- > Working temperature (°C): 150 - 160.
- > Compaction temperature (°C): 145 - 155.

APPLICATIONS

- > Hot bituminous mixtures.